

1. Product Information

Description

PC-842AL is a 100% solids, flexible, two component modified aliphatic elastomer spray applied coating material. PC-842AL is autocatalytic, containing no solvents, hardeners, or diluents. PC-842AL is used by itself or in combination with other materials to produce coatings and liners on concrete or metal substrates. Its composition makes it suitable for applications requiring color stability. PC-842AL produces an extremely tough film at any thickness. PC-842AL may be applied in all positions to any suitably prepared substrate.

PC-842AL is a superior coating material designed specifically for industrial and commercial applications receiving constant or intermittent exposure to ultraviolet light. PC-842AL is flexible, accommodating movement of the substrate, yet strong enough to remain intact under all conditions except major structural dislocations. With or without reinforcements PC-842AL may be used in transitional areas with confidence. PC-842AL may be used in interior or exterior applications.

Features

- environment friendly – no VOC
- no loss of weight
- no secondary reaction product
- highly resistant to weathering and UV
- excellent impact, abrasion and puncture resistance
- low permeability values
- applicable in temperature -15°C to +70°C
- performs in constant temperatures from -30°C to +140°C

2. Product Use

Applications

- Industrial Facilities
- Parking Garage Decks
- Walkways and Balconies
- Manufacturing Facilities
- Protecting metallic surfaces with anti-corrosive functions
- Water and Waste Water Treatment
- Food Processing Facilities
- Bottling and Canning Facilities
- Pools and Fountains
- UV Protective coating on aromatic polyurea

Coverage Rates

Mils	10	15	50	60	80
Sq. Ft.	160	107	32	27	20

The above figures are estimated coverage rates and can vary on the substrate condition and texture.

Mixing

Must be installed using a 1:1 ratio plural high-pressure, heated pump, fitted with high-pressure impingement mix spray gun. The proper necessary equipment can vary by the individual application. Contact The Polyurea Company for more support.

3. Physical Properties

Mix Ratio by Volume	1:1
Gel Time (Seconds)	30-35
VOC Content	0
Solids Content	100
Shore D Hardness, ASTM D2240	60-70
Elongation, ASTM D638, Type IV	>80
Tensile Strength (PSI), ASTM D638, Type IV	2176-2756
Tear Strength (lb./in.), ASTM D624, Die C	485 - 542
Taber Abrasion, ASTM D4060 (CS-17 Wheel, 1000 Cycles)	75 - 85

The values stated in this technical data sheet are produced under controlled laboratory conditions.

4. Preparation and Installation

Coating performance and adhesion are directly related to surface preparation. Many surface-coating failures can be attributed to improper surface preparation. Coatings are partially dependent on the integrity and structure strength of the substrate. A properly prepared substrate is free of contaminants, including but not limited to dust, dirt, oil, grease, rust, and corrosion. In certain applications, priming the substrate will be required prior to applying PC-842AL. For additional information, please review the material processing and handling guide or contact a member of The Polyurea Company technical support team.

5. Colors

RAL chart and color on request. Please contact The Polyurea Company for more information.

6. Packaging

106 Gallon Kit

53 Gallon Part-A (Isocyanate) and 53 Gallon Part-B (Resin).

Products are packaged by weight, so final package volume is a close estimation.

7. Shelf Life

A properly stored product in original, unopened factory containers, kept at a temperature above freezing should have a shelf life of 12 months from the date of shipment. Proper storage temperature is 60°F to 110°F (16°C to 45°C).

8. Safety

For in-depth information on product safety and precautions, please review the product SDS sheets. Prior to using the product, ensure that you have the proper personal protection equipment (PPE) available. This includes but is not limited to the following items:

- Safety Glasses with a splash shield
- Minimum Organic Cartridge Respirator
- Rubber or Nitrile Gloves
- Disposable or Reusable Long Sleeve Overalls
- Rubber or leather boots

Always be sure to follow the precautions listed below when using the material:

- Do Not use near high heat or open flame
- Do Not take internally
- Keep out of reach of children

9. Maintenance

No Information Provided

10. Clean-Up / Disposal

Excess material can be mixed together at the proper ratio and disposed of without restriction once cured. Product containers may be disposed of according to local, state and federal laws.

11. Warranty

At its sole election, The Polyurea Company will refund the price of or replace product it finds to be defective provided the product has been used properly and installed by a certified The Polyurea Company applicator. Except as expressly stated above, the company makes no warranty of merchantability and no warranty of fitness for any particular purpose; nor does it make any warranty, express or implied, of any nature whatsoever with respect to the product or its use. In no event shall the company be liable for delay caused by defects, loss of use, indirect, special or consequential damages, or for any charges or expenses of any nature incurred without its written consent.

12. Technical Support

For technical support, please you may send an email to support@thepolyureacompany.com.

Created Date: 03/01/2018
Revised Date: 09/19/2018
Notes: Not Available