

1. Product Information

Description

PC-740FR is a polyurea spray elastomeric that acts as a waterproofing and crack-bridging system, where also a fire proof effect is needed. PC-740FR is used with or without a geotextile membrane to protect concrete, cement screed and steel, basically all above and below ground structures e.g. parking garages, water retaining structures, steel pipes, tanks, oil separators, bulk silos, docks, truck bodies, etc. Furthermore, this system is used for sealing of flat roofs, wood coatings and in the range of industrial floors. It protects all the above from a vast range of chemicals and pollutants. PC-740FR is an extremely durable and safe solution that is designed to protect a variety of structures within a construction environment. It also provides a uniform and seamless coating that has exceptional crack-bridging and waterproofing ability. PC-740FR has excellent adhesion properties, this important fact indicates that the system is, and shall maintain its integrity. This product is ideal for complex and detailed applications. PC-740FR is also suitable when there is a high humidity factor. PC-740FR is formulated to be self-extinguishing, slight smoking and not drip.

Features

- fast reaction time
- high tensile strength
- high elongation at break
- high tear resistance
- high abrasion resistance
- flexible at low temperatures
- accepts mastic asphalt
- permeable to water vapour diffusion
- resistant to microbes
- fire retardant
- does not deteriorate over time

Limitations

Cannot be used in situations of extremely high or low pH, coupled with high temperature immersion. Contact The Polyurea Company for a more suitable system.

2. Product Use

Applications

- Waterproofing membranes
- Chemical plants
- Foam coatings
- Flexible membranes
- Flooring
- Liners
- Tank linings

Coverage Rates

Mils	10	15	50	60	80
Sq. Ft.	160	107	32	27	20

The above figures are estimated coverage rates and can vary on the substrate condition and texture.

Mixing

Must be installed using a 1:1 ratio plural high-pressure, heated pump, fitted with high-pressure impingement mix spray gun. The proper necessary equipment can vary by the individual application. Contact The Polyurea Company for more support.

3. Physical Properties

Mix Ratio by Volume	1:1
Gel Time (Seconds), ASTM D1640	6-8
Tack-Free Time (Seconds), ASTM D1640	45
VOC Content	0
Solids Content	100
Shore A Hardness, ASTM D2240	-
Shore D Hardness, ASTM D2240	35 - 40
Elongation, ASTM D638, Type IV	275 - 295
Tensile Strength (PSI), ASTM D638, Type IV	1450-1595
Tear Strength (lb./in.), ASTM D624, Die C	400 - 542
Taber Abrasion, mg wt loss, ASTM D4060 (CS-17 Wheel, 1000 Cycles)	100 - 115
Reaction to fire (class) - EN 13501-1:2005	B s2 d0

The values stated in this technical data sheet are produced under controlled laboratory conditions.

4. Preparation and Installation

Coating performance and adhesion are directly related to surface preparation. Many surface-coating failures can be attributed to improper surface preparation. Coatings are partially dependent on the integrity and structure strength of the substrate. A properly prepared substrate is free of contaminants, including but not limited to dust, dirt, oil, grease, rust, and corrosion. In certain applications, priming the substrate will be required prior to applying PC-740FR. For additional information, please review the material processing and handling guide or contact a member of The Polyurea Company technical support team.

5. Colors

PC-740FR comes in 3 standard colors: Tan, Black, and Gray. If you need a special color for a specific application, please contact The Polyurea Company for more information.

6. Packaging

106 Gallon Kit

53 Gallon Part-A (Isocyanate) and 53 Gallon Part-B (Resin).

Products are packaged by weight, so final package volume is a close estimation.

7. Shelf Life

A properly stored product in original, unopened factory containers, kept at a temperature above freezing should have a shelf life of 12 months from the date of shipment. Proper storage temperature is 60°F to 110°F (16°C to 45°C).

8. Safety

For in-depth information on product safety and precautions, please review the product SDS sheets. Prior to using the product, ensure that you have the proper personal protection equipment (PPE) available. This includes but is not limited to the following items:

- Safety Glasses with a splash shield
- Minimum Organic Cartridge Respirator
- Rubber or Nitrile Gloves
- Disposable or Reusable Long Sleeve Overalls
- Rubber or leather boots

Always be sure to follow the precautions listed below when using the material:

- Do Not use near high heat or open flame
- Do Not take internally
- Keep out of reach of children

9. Maintenance

No Information Provided

10. Clean-Up / Disposal

Excess material can be mixed together at the proper ratio and disposed of without restriction once cured. Product containers may be disposed of according to local, state and federal laws.

11. Warranty

At its sole election, The Polyurea Company will refund the price of or replace product it finds to be defective provided the product has been used properly and installed by a certified The Polyurea Company applicator. Except as expressly stated above, the company makes no warranty of merchantability and no warranty of fitness for any particular purpose; nor does it make any warranty, express or implied, of any nature whatsoever with respect to the product or its use. In no event shall the company be liable for delay caused by defects, loss of use, indirect, special or consequential damages, or for any charges or expenses of any nature incurred without its written consent.

12. Technical Support

For technical support, please you may send an email to support@thepolyureacompany.com.

Created Date: 03/01/2018

Revised Date: 09/19/2021

Notes: Not Available

Conforming to the requirements of



9001:2015 14001:2015 45001:2018